



ZHEHENG STEEL

Wenzhou Zheheng Steel Industry Co.,Ltd  
stainless-steelseamlesspipe.com

## Seamless 21mm Duplex Steel Pipe

Our Product Introduction

for more products please visit us on [stainless-steelseamlesspipe.com](http://stainless-steelseamlesspipe.com)

### Basic Information

- Place of Origin: CHINA
- Brand Name: zheheng
- Certification: ISO9001 PED
- Model Number: 21mm
- Minimum Order Quantity: Negotiable
- Price: Negotiable
- Packaging Details: In bundles with waterproof material, or wooden crate packing
- Delivery Time: 30 DAYS
- Payment Terms: L/C, T/T, D/A, D/P
- Supply Ability: 50TONS/30DAYS



### Product Specification

- Steel Grade: 2304 / 1.4362 / X2CRNIN23-4 S32520
- Standard: A789
- Type: Seamless
- Technique: Cold Drawing
- Lead Time: 30 Days
- Material: 1.4362
- Highlight: 1.4362 duplex pipe, A789 duplex pipe



### More Images



## Product Description

### 2304 / 1.4362 / X2CRNIN23-4 S32520 Duplex Steel Pipe / A789 Seamless and Welded Ferritic/Austenitic Stainless

#### Details for description:

Material:

2304 / 1.4362 / X2CRNIN23-4 S32520 .310S.316.316L.321.430.430A.309S.2205.2507.

2520.430.410.440.904Lect. Or Customized

Standard: GB, AISI, ASTM, ASME, EN, BS, DIN, JIS

Size: ANSI /ASME size is under, other standard of size is for ready choice, O.D.:0.23"to 48"(5.8-1219mm)W.T.:0.04"to 2"(1.0-50.8mm)

Length: Max.18 Meter,NPS 1/8"-48" Schedule:5/5S,10/10S,20/20S,40/40S,80/80S,120/120S,160/160S according to ANSI B36.19/36.10

Surface: Satin Finish(180#.240#.320#),Bright Finish(400#.600#,mirror),Mill Finish(2B),Hairline-Finish(HL/Brushed),Ti-gold, Glossy matt,dull and so on.

#### 2304 / 1.4362 / X2CRNIN23-4 S32520 Super Duplex Steel Pipe chemical composition

A 789/A 789M - 05a

TABLE 1 Chemical Requirements<sup>a</sup>

UNS Designation <sup>a</sup>	C	Mn	P	S	Si	Ni	Cr	Mo	N	Cu	Others
S31200	0.030	2.00	0.045	0.030	1.00	5.5-6.5	24.0-26.0	1.20-2.00	0.14-0.20	---	---
S31260	0.030	1.00	0.030	0.030	0.75	5.5-7.5	24.0-26.0	2.5-3.5	0.10-0.30	0.20-0.80	W 0.10-0.50
S31500	0.030	1.20-2.00	0.030	0.030	1.40-2.00	4.3-6.2	18.0-19.0	2.50-3.00	0.05-0.1	---	---
S31803	0.030	2.00	0.030	0.020	1.00	4.5-6.5	21.0-23.0	2.5-3.5	0.08-0.20	---	---
S32001	0.030	4.00-6.00	0.040	0.030	1.00	1.0-3.0	19.5-21.5	0.60	0.05-0.17	1.00	---
S32003	0.030	2.00	0.030	0.020	1.00	3.0-4.0	19.5-22.5	1.50-2.00	0.14-0.20	---	---
S32101	0.040	4.0-6.0	0.040	0.030	1.00	1.35-1.70	21.0-22.0	0.10-0.80	0.20-0.25	0.10-0.80	---
S32205	0.030	2.00	0.030	0.020	1.00	4.5-6.5	22.0-23.0	3.0-3.5	0.14-0.20	---	---
S32304	0.030	2.50	0.040	0.040	1.00	3.0-5.5	21.5-24.5	0.05-0.60	0.05-0.20	0.05-0.60	---
S32520	0.030	1.50	0.035	0.020	0.80	5.5-8.0	23.0-25.0	3-5	0.20-0.35	0.50-3.00	---
S32550	0.04	1.50	0.040	0.030	1.00	4.5-6.5	24.0-27.0	2.0-3.9	0.10-0.25	1.50-2.50	---
S32750	0.030	1.20	0.035	0.020	0.80	6.0-8.0	24.0-26.0	3.0-5.0	0.24-0.32	0.50	---
S32760	0.05	1.00	0.030	0.010	1.00	6.0-8.0	24.0-26.0	3.0-4.0	0.20-0.30	0.50-1.00	W 0.50-1.00
											40 min <sup>b</sup>
S32808	0.030	1.10	0.030	0.030	0.50	7.0-8.2	27.0-27.9	0.80-1.20	0.30-0.40	---	W 2.10-2.50
S32900	0.08	1.00	0.040	0.030	0.75	2.5-5.0	23.0-28.0	1.00-2.00	---	---	---
S32906	0.030	0.80-1.50	0.030	0.030	0.50	5.8-7.5	28.0-30.0	1.50-2.60	0.30-0.40	0.80	---
S32950	0.030	2.00	0.035	0.010	0.60	3.5-5.2	26.0-29.0	1.00-2.50	0.15-0.35	---	---
S36274	0.030	1.00	0.030	0.020	0.80	6.0-8.0	24.0-26.0	2.5-3.5	0.24-0.32	0.20-0.80	W 1.50-2.50
S39277	0.025	0.80	0.025	0.002	0.80	6.5-8.0	24.0-26.0	3.00-4.00	0.23-0.33	1.20-2.00	W 0.80-1.21

#### Details description :

Application:	Decoration, construction and upholstery, etc
Package:	Each tube in a plastic bag with size label outside and pack in small bundles or according to customer request
Lead Time:	7-10days for one FCL Or according to order list detail
Payment:	A: 100% T/T advance. ( For small order.) B: 30% T/T and balance against copy of documents. C: 30% T/T advance, balance L/C at sight D: 30% T/T , balance L/C usance E: 100% L/C usance. F: 100% L/C at sight.
Sample:	we could offer the sample for free charge but do not pay the cost of freight.

#### Permissible Variations in Dimensions

1 Variations in outside diameter, wall thickness, and length from those specified shall not exceed the amounts prescribed in Table 5.

2 The permissible variations in outside diameter given in Table 5 are not sufficient to provide for ovality in thin-walled tubes, as defined in the table. In such tubes, the maximum and minimum diameters at any cross section shall deviate from the nominal diameter by no more than twice the permissible variation in outside diameter given in Table 5; however, the mean diameter at that cross section must still be within the given permissible variation.

#### Product show:





ZHEHENG STEEL

**Wenzhou Zheheng Steel Industry Co.,Ltd**



15858820108



[sales@zhehengsteel.com](mailto:sales@zhehengsteel.com)



[stainless-steelseamlesspipe.com](http://stainless-steelseamlesspipe.com)

No999 .wenzhou airport wenzhou city,zhejiang china